



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61L 27/00, C08G 18/42	A1	(11) International Publication Number: WO 99/22780 (43) International Publication Date: 14 May 1999 (14.05.99)
(21) International Application Number: PCT/SE98/01869 (22) International Filing Date: 19 October 1998 (19.10.98) (30) Priority Data: 9704003-4 3 November 1997 (03.11.97) SE (71) Applicant (for all designated States except US): ARTIM-PLANT DEVELOPMENT ARTDEV AB [SE/SE]; Hulda Mellgrens gata 5, S-421 32 Västra Frölunda (SE). (72) Inventors; and (75) Inventors/Applicants (for US only): FLODIN, Per [SE/SE]; Ryetvägen 5, S-436 55 Hovås (SE). GISSELFÄLT, Katrin [SE/SE]; Vidblicksgatan 5, S-412 57 Göteborg (SE). (74) Agents: GRAUDUMS, Valdis et al.; Albiņš Patentbyrå Göteborg AB, P.O. Box 142, S-401 22 Göteborg (SE).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: SHAPED BODIES FOR USE AS IMPLANTS IN HUMAN MEDICINE AND METHOD FOR THE PRODUCTION OF SUCH SHAPED BODIES (57) Abstract The present invention relates to shaped bodies for use as implants in human and veterinary medicine as pins, screws, discs, ligament fixtures and the like. The shaped bodies consist of polyurethanes having ester links which can be hydrolysed in a human body and which give hydrolysis fragments which are sufficiently small to be resorbed in the human body. The shaped bodies are characterised in that the polymer is a network polymer which substantially lacks urea groups. The invention also relates to a method for the production of the shaped bodies which means that a suitable starting mixture according to the invention is introduced in moulds and cured at a temperature of 70-150 °C in the absence of catalysts and at a temperature of 30-100 °C in the presence of a catalyst.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE:

Shaped bodies for use as implants in human medicine and method for the production of such shaped bodies

5 TECHNICAL FIELD:

The present invention relates to shaped bodies which are to be used as implants in human and veterinary medicine and which primarily consist of pins, screws, discs, ligament fixtures etc. The shaped bodies consist of cured polymer material based on polyurethanes. The invention also comprises a method for the production of
10 the shaped bodies.

PRIOR ART:

Both implants and transplants are now commonly used within the medical field. When a human body or an animal is injured as a result of some illness, a damaged
15 organ must often be replaced temporarily or permanently by some kind of implant. The implants may be rigid and be in the form of pins, screws, discs or the like and the material in such implants is usually titanium, steel or the like. The implants may also be soft and, for example, be in the form of pipes which are intended to replace veins or drain out some kind of body fluid and they are then
20 usually made of thermoplastic materials.

Such a soft but resistant implant consists of a polyurethane material and is present in the form of threads or fabric intended to sew together or repair broken ligaments. After the ligaments have been sewn together with this implant, the
25 natural tissue will grow and repair the broken place, whereas the implant slowly disappears and is resorbed by the body fluids. This implant is accordingly temporary and the slow disintegration thereof occurs due to the fact that the polymer chains contain suitable hydrolysable ester groups which are split and which are so closely arranged that the fractions after the hydrolysis are so
30 small that they can be excreted from and/or be metabolised in the body. Such an implant is described in the Swedish patent 9504495-4

It is of decisive importance for an implant that it is biocompatible, i.e. that it can be accepted by the tissues of the body and does not injuriously affect them. It
35 must also have such properties that it, for example, can replace or support the functions of the damaged organs. Some implants, such as titanium screws for teeth, are intended to be permanent and shall remain in the patient as long as he or she lives. Other implants, which per se are permanent in nature, are however intended to be removed after a long or short period of time

THE TECHNICAL PROBLEM:

- In connection with such implants as pins, screws, discs etc. which are not intended to remain permanently in the patient, a second operation will accordingly be needed after the first operation when the implant is introduced in the body, namely an operation to remove the implant. After the removal of such an implant, a cavity is formed which functions as an indication of fracture until new tissue has been formed. This can take from several months to a couple of years and substantially prolongs the time for complete healing.
- 10 The metallic implants such as steel and titanium also have a much higher coefficient of elasticity than, for example, human bone. This leads to a reduction in the normal load on the neighbouring tissues, which results in less good healing and sometimes degeneration of the tissue.
- 15 It has long been a desire to bring about a rigid implant for joining of, for example, bones, which implant does not have to be removed later by re-operation and which has a coefficient of elasticity which is comparable to that of the bone.

THE SOLUTION:

- 20 By means of the present invention, the above problem has been solved, making re-operation unnecessary and shaped bodies for use as implants in human medicine as pins, screws, discs, ligament fixtures etc. consisting of polyurethanes with ester links which are hydrolysable in a human body and which give hydrolysis fragments sufficiently small to be resorbed in the human body is
- 25 brought about which shaped bodies are characterised in that the polymer is a network polymer which substantially lacks urea groups.

- According to the invention the ester links should be located so closely that the hydrolysis fragments obtain a molecular weight of at most 1500 Dalton,
- 30 preferably at most 1000 Dalton by complete hydrolysis.

- The invention also comprises a method for the production of shaped bodies, which method is characterised in that a complete mixture of starting materials for forming network polymers of polyurethane containing hydrolysable ester groups
- 35 and being substantially free from urea groups is introduced in suitable moulds and heated there to a curing temperature during a sufficient length of time to form the form-resistant shaped bodies. The final curing can later take place in a heating furnace.

To make compact shaped bodies according to the invention, it is necessary that water is removed from the reaction mixture, preferably by means of a thin film air evaporator or vacuum.

- 5 If, however, porous shaped bodies according to the invention are desired then water or some other kind of cell-forming material may be added in controlled amounts before the curing.

10 According to the invention the curing in the moulds should be carried out a temperature of 70-150°C in the absence of a catalyst.

However, if a catalyst is used, the curing in the moulds should be performed at a temperature of 30-100°C. Many substances which catalyse the reaction are known, for example aliphatic and aromatic tertiary amines, organometallic
15 compounds, alkali metal salts of carboxyl acids and phenols, etc. As an example, N-ethylmorpholine, dibutyl tin dilaurate can be mentioned. Besides these, compounds exist which both participate in the reaction and catalyse the reaction, for example triethanolamine.

20 According to the invention, the mixture of starting materials consist, of linear prepolymers having isocyanate end groups and branched polyols, of isocyanate end-terminated polyol prepolymers and diols and/or polyols, of di-isocyanate and diols and polyols or of polyisocyanate and di- or polyols or mixtures thereof.

25 According to the invention, it is suitable that the hydrolysable ester groups originate from di- or polyols which may be monoesters, oligo- or polyesters.


According to the invention the di- or polyols in the polyester part suitably consist of ethylene glycol, diethylene glycol, propylene glycol, 1,4-butane diol,
30 polyethylene glycol, oligo- and polytetramethylene oxide glycol, glycerol, trimethylol propane, pentaerythritol, sorbitol, xylitol, glycerol monoallylether and trimethylol propane monoallyl ether.

According to the invention, the acids in the ester groups consist suitably of
35 adipinic acid, succinic acid, glutaric acid, maleinic acid, fumaric acid, bis-carboxymethylethylene glycol, citric acid, tris-carboxymethyl trimethyl propane, bis-carboxymethyl glycerol.

DETAILED DESCRIPTION OF THE INVENTION

The shaped bodies according to the invention consist, as mentioned above, of polyurethanes having certain properties such as adapted suitable hardness having an elasticity coefficient which corresponds to that part of the body, for example a bone part, which is to be supported or replaced and which can be decomposed hydrolytically, whereupon fragments which are sufficiently small for resorption into the human body are obtained. The materials according to the invention must also be biocompatible.

The most important, but not the only, way to produce urethanes is by reaction between an isocyanate and an alcohol. A diisocyanate and a diol in approximately equivalent amount gives a linear polyurethane, whereas a diisocyanate reacted with a polyol gives a network polymer. Such a product is also obtained with polyisocyanates and diols or polyols. Network polymers according to the present invention comprise primarily diisocyanates and polyols. The latter can consist of mixtures of diols and polyols.



Polyurethanes are characterised by urethane groups, $-\text{OCONH}-$, which are separated partly by that radical, R_1 , which originate from the diisocyanate and partly that radical, R_2 , which originate from the diol or the polyol. R_2 is the one which allows for the largest selection of structures. Theoretically, the isocyanate may also be varied within very wide limits but practically the number is limited due to the difficulty in synthesising isocyanates. This results in that in practice only commercially available isocyanates are used.

R_2 originates from diols or polyols and must contain ester groups to be hydrolysable according to the invention. The number of ester groups must be so large that the fragments obtained after complete hydrolysis have a size which is lower than the set limit of 1500. The diols or polyols used may be oligo- or polyesters and may have very varying composition. Also the diol or the polyol component may be mixtures of diols or polyols. Both the diol and the acid component may vary within wide limits and be mixtures of diols and/or acids. Ester groups may also be present in R_1 .

Examples of usable diols and polyols in the polyester part of R_2 may be ethylene glycol, diethylene glycol, propylene glycol, 1,4-butane diol, polyethylene glycol.

oligo- and polytetramethylene oxide glycol, glycerol, trimethylol propane, pentaerythritol, sorbitol, xylitol, glycerol monoallyl ether, glycerine mono-glycidyl ether, trimethylol propane monoallyl ether. They should not contain functional groups which can react with isocyanites at the later chain extension.

5

Usable dibasic or polybasic acids in the ester/polyester part of R_2 are for instance adipinic acid, succinic acid, glutaric acid, maleinic acid, fumaric acid, bis-carboxymethylethylene glycol, citric acid, tris-carboxymethyltrimethylol propane, bis-carboxymethylglycerol.

10

It is very important that the substances in the starting mixture are completely blendable at least at the temperature at which the network forming occurs. If not, an uneven product will be obtained. The starting mixture can consist of a mixture of a linear prepolymer with a branched polyol, of a mixture of a polyol prepolymer with a diol and/or a polyol, of a mixture of a diisocyanate with a diol and/or polyol or a mixture of a polyisocyanate with a diol or a polyol. It is of course possible to combine one or more of these mixtures.

15

The production of the shaped bodies is carried out by blending the starting materials and introducing them into a mould and heating them therein. The mould can be formed according to the desired the end product, for example for making a screw or a disc or it can give a blank for further machining by, for example, cutting. A technique for the production of blanks is so-called pultrusion by means of which method a continuous rod is formed.

20

25

According to the invention, it is important that, if the aim is to obtain a homogeneous material, all water is removed from the reaction mixture. This may be done by carrying out the mixing in a thin layer evaporator or treating the mixture in such an evaporator after the mixing but before the curing. By letting vacuum act on a thin film, any remaining water will be removed from the mixture which during the reaction may cause bubbles to form.

30

If a porous material (cellular plastic) is desired, such a material may be made by the addition of a controlled amount of water or some other cell-forming material. The technique for this is well known from cellular plastics technology. In addition to water, low-temperature boiling solvents and diazocompounds, among others, may be used as cell-formers. The techniques for regulating the amount of cells, the size of the cells, the proportion of open or closed cells etc., are well known

35

Since the implants shall be present in a human or an animal body during long periods and decomposed there, it is very important that no poisonous or unfavourable substances are released. It is therefore preferable that the forming of the three-dimensional network, i.e. the curing in the moulds, is carried out without the aid of releasable catalysts. The temperature in the moulds should therefore be, according to the invention, about 70-150°C when isocyanate groups react with hydroxyl groups. It may be lower, for example 30-100°C, in the presence of catalysts built into the network, such as triethanole amine.

The time for curing may vary within wide limits depending on the reactivity of the components, but it varies from a few minutes to more than one day. The time which the mixture needs to be in the moulds may only be so long that the shaped body obtains its final shape and can be taken out, further curing being able to be performed in a heating chamber or the like so that the moulds once again can be filled with starting material.

However, it is possible to use catalysts in the starting material if they fulfil the demand for biocompatibility. Such catalysts may consist of tertiary amines such as N-methyl morpholin. Great care with the catalysts is important since the implant is to be used in living beings. Non-catalyst reactions or reactions where the catalyst is build into the network are therefore preferable. In that case the fragments containing the catalyst remainders must be atoxic after hydrolysis.

As mentioned above, the decomposition of the network polymers occurs primarily by hydrolysis of the ester bonds. Between every cross-link point in the network there are such ester groups so that the hydrolysis fragments will consist of sufficiently low-molecular substances. If oligo- or polyesters are part of the polymer then di- or poly acids and di- or polyols will also be created. Several conceivable such substances can be metabolised and thereby be excreted as carbon dioxide and water. The larger fragments are excreted via urine and/or faeces. It is accordingly important that the molecular weight is so low that the substances can pass the membranes of the body

EXAMPLES:

35

1. 18.82 g of a prepolymer produced from a dicyclohexylmethane 4,4-diisocyanate (H₁₂MDI) and polycaprolactone (molecular weight 530 g/mol) was de-watered in vacuum in a thin film evaporator at 80°C during 3 hours. Thereafter, 1.37 g 2-ethyl-2-(hydroxymethyl)-1,3-

propane diol was added. Admixture and further de-watering were carried out at 80°C during 30 minutes. The homogeneous mixture was weighed out into cylindrical moulds as batches which were heated to 120°C during 20 hours. The cylinders obtained had a hardness of 70 Shore D

2. 8.25 g of a branched polyester polyol of trimethylol propane, adipinic acid and diethylene glycol having a hydroxyl equivalent weight of 229 g/mol was mixed with 3.03 g hexamethylene diisocyanate under vacuum in a thin film evaporator at 90°C during 30 minutes whereupon a homogeneous mixture was obtained. It was weighed out into cylindrical moulds and heated to 120°C during 20 hours. The product had a hardness of 40 Shore D.
3. 14.95 g of a prepolymer produced from 4,4'-diphenylmethane diisocyanate (MDI) and polycaprolactone (molecular weight 530 g/mol) was de-watered in vacuum in a thin film evaporator at 80°C during 3 hours. Thereafter 1.2 g unhydrous glycerol was added. Admixture and further de-watering was carried out at 80°C during 10 minutes. The homogeneous mixture was weighed out into cylindrical moulds which were heated to 80°C during 3 hours. The cylinders obtained had a hardness of 70 Shore D.
4. 15.72 g of a prepolymer produced from dicyclohexylmethane-4,4'-diisocyanate (H₁₂MDI) and polycaprolactone (molecular weight 530 g/mol) was de-watered in vacuum in a thin film evaporator at 90°C during 3 hours. Thereafter 1.47 g triethanol amine was added and the de-watering was continued for a further 30 minutes at 90°C. The homogeneous mixture was weighed out into cylindrical moulds which were heated at 100°C during 20 hours. The cylinders obtained had a hardness of 60 Shore D.

The invention is not limited to the above-mentioned embodiment examples but it can be varied in different ways within the scope of the patent claims.

5 CLAIMS:

- 1 Shaped bodies for use as implants in human medicine as pins, screws, discs, ligament fixtures etc, consisting of polyurethanes with ester links which can be hydrolysed in a human body and which give hydrolysis fragments sufficiently
10 small to be resorbed in the human body, characterised in that the polymer is a network polymer which substantially lacks urea groups.
- 2 Shaped bodies according to claim 1, characterised in that the ester links are so closely located that the hydrolysis fragments will have a
15 molecular weight of at most 1500 Dalton, preferably at most 1000 Dalton.
- 3 Method for the production of shaped bodies according to claim 1 or 2, characterised in that a complete mixture of starting materials for making network polymers of polyurethane comprising hydrolysable ester groups and
20 substantially free from urea groups is introduced in suitable moulds and heated there at curing temperature during a sufficient length of time to form a shaped body.
- 4 Method according to claim 3, characterised in that to form
25 compact bodies, water is removed from the reaction mixture preferably by means of a thin film evaporator and vacuum.
- 5 Method according to claim 3, characterised in that for making porous bodies, water or some other cell-forming material is added in a controlled
30 amount.
- 6 Method according to any one of claims 3-5, characterised in that the curing in the moulds is carried out at a temperature of 70-150°C in the absence of catalysts
35
- 7 Method according to any one of claims 3-5, characterised in that the curing in the moulds is carried out at a temperature of 30-100°C in the presence of catalysts such as tertiary amines, for example N-methylmorpholin

8. Method according to any one of the claims 3-7, characterised in that the mixture of the starting materials consists of linear prepolymers with isocyanate end groups and branched polyols, of isocyanate terminated polyolprepolymers and diols and/or polyols, of diisocyanate and diols and/or polyols or of polyisocyanate and diols or polyols or mixtures thereof

9. Method according to claim 8, characterised in that the hydrolysable ester groups originate from diols or polyols which can be monoesters, oligo- or polyesters.

10

10. Method according to claim 8 or 9, characterised in that the diols or polyols in the polyester part are ethylene glycol, diethylene glycol, propylene glycol, 1,4-butane diol, polyethylene glycol, oligo- and polytetramethylene oxide glycol, glycerol, trimethylol propane, pentaerythritol, sorbitol, xylitol, glycerol monoallylether, trimethylol propane monoallylether

15

11. Method according to claim 8 or 9, characterised in that the acids in the ester groups consist of adipinic acid, succinic acid, glutaric acid, maleinic acid, fumaric acid, bis-carboxymethylethylene glycol, citric acid, tris-carboxymethyltrimethyl propane, bis-carboxymethyl glycerol

20

INTERNATIONAL SEARCH REPORT

International application No.
PCT/SE 98/01869

A. CLASSIFICATION OF SUBJECT MATTER		
IPC6: A61L 27/00, C08G 18/42 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC6: A61L, C08G		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
SE,DK,FI,NO classes as above		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 8905830 A1 (STICHTING BIOMAT), 29 June 1989 (29.06.89) --	1-11
A	WO 9409048 A1 (RIJKSUNIVERSITEIT TE GRONINGEN), 28 April 1994 (28.04.94) --	1-11
A	WO 9722643 A1 (FLODIN, PER), 26 June 1997 (26.06.97) -- -----	1-11
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input checked="" type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
18 February 1999		22 -02- 1999
Name and mailing address of the ISA/ Swedish Patent Office Box 5055, S-102 42 STOCKHOLM Facsimile No. +46 8 666 02 86		Authorized officer Jack Hedlund Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

Information on patent family members

02/02/99

International application No.

PCT/SE 98/01869

Patent document cited in search report			Publication date	Patent family member(s)		Publication date
WO	8905830	A1	29/06/89	EP	0417095 A	20/03/91
				NL	8703115 A	17/07/89
WO	9409048	A1	28/04/94	AU	5377894 A	09/05/94
				EP	0665855 A	09/08/95
WO	9722643	A1	26/06/97	AU	1154797 A	14/07/97
				CZ	9801793 A	11/11/98
				EP	0866816 A	30/09/98
				NO	982703 A	14/07/98
				SE	505703 C	29/09/97
				SE	9504495 A	16/06/97

